



Tel: 0116 275 4720 Fax: 0116 275 4721
Email: sales@edcoseal.co.uk Web: www.edcoseal.co.uk

EPDM 70
TEST REPORT

A COLOUR BLACK
B OPERATING TEMP RANGE (-) 55 TO (+) 150 DEG C
C COMPLYS TO ASTM D2000 M4CA710 B35 F19

D PHYSICAL PROPERTIES PRESS CURE @ 170 DEG C X 10 MIN
POST CURE @ 230 DEG C X 24 HOURS

Table with 3 columns: Property Name, Requirements, Results. Rows include Hardness Shore A, Tensile Strength MPA, Elongation %, and Specific Gravity.

E HEAT RESISTANCE TESTED AT 125 DEG C FOR 70 HOURS

Table with 3 columns: Property Name, Requirements, Results. Rows include Hardness Change (Points), Tensile Strength Change %, and Elongation Change %.

F COMPRESSION SET CURING CONDITIONS
HEAT AGING @ 125 DEG C X 22 HOURS 9

70 50

LOW TEMP BRITTLENESS TESTS AFTER 3 MINS @ -55 DEG C NON BRITTLE

PLEASE NOTE THAT THESE RESULTS ARE FOR REFERENCE PURPOSES ONLY AND EDCO SEAL AND SUPPLY LTD MAKES NO WARRANTY, EXPRESSED OR IMPLIED, THAT PARTS MANUFACTURED IN THIS COMPOUND WILL PERFORM SATISFACTORILY IN THE CUSTOMERS APPLICATION. IT IS THE CUSTOMERS RESPONSIBILITY TO TEST PARTS PRIOR TO USE.